

VAKU LIGHT



Contents	Art. No.	Qty
1.300ml + 50g Hardener	0993 140	1/8

Technical data		
Chemical Base	Unsaturated polyester resin, light weight inert, pigments	
Colour	White	
Weight	1.2 kg/L at 20°C	
Mix life with 2-3% Hardener at 20°C	5 minutes	
Heat resistance	80°C at 100°C	
Drying time	25 minutes at 20°C in galvanised sheets wait 1 hour to 2 hours before sanding	
Application temperature	More than 5°C	
Dry sanding	P80 to P280	
Repainting	All bases used in automotive	
Types of veneers	Steel sheets, galvanized, electrozinc, aluminum, wood and parts with polyester base	
Storage conditions	At 20°C in airtight container	

Multi-metal polyester putty extremely easy to sand

- Light loads. Great ease of sanding without clogging the disc.
- Good surface finish.
- It allows you to start sanding with a less coarse abrasive.
- Easy and fast application. Perfect viscosity and mixed.
- It allows to apply a lot of quantity at one time with comfort.

Applications

As filler in sheet metal and paint shops, bodywork, industrial vehicles, marine, motorcycles, etc.